



HIGH PERFORMANCE Eco-FABRIC FOR VERTICAL SURFACES

Wallcoverings • Panel Systems • Partitions

Utilizing a combination of pre-consumer and post-consumer recycled polyester to create unique performance yarns, Hytex Industries introduces our newest collection of vertical surface textiles for the commercial market.

DOMINO

SPECIFICATIONS

| <u>CONTENT</u> | <u>BACKING</u> | <u>FINISH</u> | <u>WEIGHT</u> | <u>WIDTH</u> | <u>ROLL SIZE</u> |
|--|----------------|---|---------------|--------------|------------------|
| · 100% recycled polyester · 24% post-consumer · 76% pre-consumer | acrylic latex | Crypton® 'Green' Soil & Stain Repellant | 18 oz. | 54" | 50 yards |

FLAMMABILITY

Passes: NFPA 286
Class A / ASTM E-84
Passes: Cal 117
Passes: Vertical Burn

ABRASION RESISTANCE

(ASTM D-4157-02)
100,000 double rubs

COLOR FASTNESS TO LIGHT

(AATCC-16A)
Class 5.0 / 100 hrs.

ENVIRONMENTAL

does not contain:

- pvc
- chlorene
- plasticizers
- heavy metals
- formaldehyde
- ozone depleting substances
- volatile organic chemicals (voc's)

conserving natural resources:

- diverts waste from landfills
- offsets the need to refine new crude oil
- requires less energy to produce

REPREVE®
recycled yarns by unifi

© Hytex Industries, Inc. 2009 All rights reserved.

©2008 CRYPTON, Inc. CRYPTON and the planet logo are registered trademarks of CRYPTON, Inc. U.S. patent 5,565,265 and other U.S. and global patents issued and pending.

REPREVE is a registered trademark of Unifi, Inc.



HIGH PERFORMANCE Eco-FABRIC FOR VERTICAL SURFACES

Wallcoverings • Panel Systems • Partitions

Utilizing a combination of pre-consumer and post-consumer recycled polyester to create unique performance yarns, Hytex Industries introduces our newest collection of vertical surface textiles for the commercial market.

GRAPH PAPER

SPECIFICATIONS

| <u>CONTENT</u> | <u>BACKING</u> | <u>FINISH</u> | <u>WEIGHT</u> | <u>WIDTH</u> | <u>ROLL SIZE</u> |
|------------------------------------|----------------|---|---------------|--------------|------------------|
| · 100% polyester | acrylic | Crypton® 'Green' Soil & Stain Repellant | 18 oz. | 54" | 50 yards |
| <u>80% RECYCLED CONTENT</u> | | | | | |
| · 31% post-consumer | | | | | |
| · 49% pre-consumer | | | | | |

FLAMMABILITY

Passes: NFPA 286
Class A / ASTM E-84
FS: 25
SD: 25
Passes: Cal 117
Passes: Vertical Burn

ABRASION RESISTANCE

(ASTM D-4157-02)
100,000 double rubs

COLOR FASTNESS TO LIGHT

(AATCC-16A)
Class 5.0 / 100 hrs.

ENVIRONMENTAL

does not contain:

- pvc
- chlorene
- plasticizers
- heavy metals
- formaldehyde
- ozone depleting substances
- volatile organic chemicals (voc's)

conserving natural resources:

- diverts waste from landfills
- offsets the need to refine new crude oil
- requires less energy to produce

REPREVE®
recycled yarns by unifi

©Hytex Industries, Inc. 2010 All rights reserved.

©2008 CRYPTON, Inc. CRYPTON and the planet logo are registered trademarks of CRYPTON, Inc. U.S. patent 5,565,265 and other U.S. and global patents issued and pending.

REPREVE is a registered trademark of Unifi, Inc.



HIGH PERFORMANCE Eco-FABRIC FOR VERTICAL SURFACES

Wallcoverings • Panel Systems • Partitions

Utilizing a combination of pre-consumer and post-consumer recycled polyester to create unique performance yarns, Hytex Industries introduces our newest collection of vertical surface textiles for the commercial market.

IMPERIAL

SPECIFICATIONS

| <u>CONTENT</u> | <u>BACKING</u> | <u>FINISH</u> | <u>WEIGHT</u> | <u>WIDTH</u> | <u>ROLL SIZE</u> |
|---------------------------|----------------|---|---------------|--------------|------------------|
| · 100% recycled polyester | acrylic | Crypton® 'Green' Soil & Stain Repellant | 15 oz. | 54" | 50 yards |
| <u>RECYCLED</u> | | | | | |
| · 43% post-consumer | | | | | |
| · 57% pre-consumer | | | | | |

FLAMMABILITY

Passes: NFPA 286
Class A / ASTM E-84
FS: 25
SD: 25
Passes: Cal 117
Passes: Vertical Burn

ABRASION RESISTANCE

(ASTM D-4157-02)
100,000 double rubs

COLOR FASTNESS TO LIGHT

(AATCC-16A)
Class 5.0 / 100 hrs.

ENVIRONMENTAL

does not contain:

- pvc
- chlorene
- plasticizers
- heavy metals
- formaldehyde
- ozone depleting substances
- volatile organic chemicals (voc's)

conserving natural resources:

- diverts waste from landfills
- offsets the need to refine new crude oil
- requires less energy to produce

REPREVE®
recycled yarns by unifi



CRYPTON®

WALL FABRICS

HIGH PERFORMANCE Eco-FABRIC FOR VERTICAL SURFACES

Wallcoverings • Panel Systems • Partitions

Utilizing a combination of pre-consumer and post-consumer recycled polyester to create unique performance yarns, Hytex Industries introduces our newest collection of vertical surface textiles for the commercial market.

INTUITION SPECIFICATIONS

| <u>CONTENT</u> | <u>BACKING</u> | <u>FINISH</u> | <u>WEIGHT</u> | <u>WIDTH</u> | <u>ROLL SIZE</u> |
|--|----------------|---|---------------|--------------|------------------|
| · 70% polyester · 30% olefin | acrylic | Crypton® 'Green' Soil & Stain Repellant | 16 oz. | 54" | 50 yards |
| <u>RECYCLED</u> · 30% pre-consumer (olefin) | | | | | |

FLAMMABILITY

Passes: NFPA 286
Class A / ASTM E-84
FS: 20
SD: 50
Passes: Cal 117
Passes: Vertical Burn

ABRASION RESISTANCE

(ASTM D-4157-02)
100,000 double rubs

COLOR FASTNESS TO LIGHT

(AATCC-16A)
Class 5.0 / 100 hrs.

ENVIRONMENTAL

does not contain:

- pvc
- chlorene
- plasticizers
- heavy metals
- formaldehyde
- ozone depleting substances
- volatile organic chemicals (voc's)

conserving natural resources:

- diverts waste from landfills
- offsets the need to refine new crude oil
- requires less energy to produce

© Hytex Industries, Inc. 2010 All rights reserved.

©2008 CRYPTON, Inc. CRYPTON and the planet logo are registered trademarks of CRYPTON, Inc. U.S. patent 5,565,265 and other U.S. and global patents issued and pending.

REPREVE is a registered trademark of Unifi, Inc.



HIGH PERFORMANCE Eco-FABRIC FOR VERTICAL SURFACES

Wallcoverings • Panel Systems • Partitions

Utilizing a combination of pre-consumer and post-consumer recycled polyester to create unique performance yarns, Hytex Industries introduces our newest collection of vertical surface textiles for the commercial market.

SHIMMER

SPECIFICATIONS

| CONTENT | BACKING | FINISH | WEIGHT | WIDTH | ROLL SIZE |
|--|---------|---|--------|-------|-----------|
| · 67% polyester · 33% olefin | acrylic | Crypton® 'Green' Soil & Stain Repellant | 15 oz. | 54" | 50 yards |
| 43 % RECYCLED CONTENT | | | | | |
| · 10% post-consumer (polyester) · 33% pre-consumer (olefin) | | | | | |

FLAMMABILITY

Passes: NFPA 286
Class A / ASTM E-84
FS: 20
SD: 50
Passes: Cal 117
Passes: Vertical Burn

ABRASION RESISTANCE

(ASTM D-4157-02)
100,000 double rubs

COLOR FASTNESS TO LIGHT

(AATCC-16A)
Class 5.0 / 100 hrs.

ENVIRONMENTAL

does not contain:

- pvc
- chlorene
- plasticizers
- heavy metals
- formaldehyde
- ozone depleting substances
- volatile organic chemicals (voc's)

conserving natural resources:

- diverts waste from landfills
- offsets the need to refine new crude oil
- requires less energy to produce

REPREVE®
recycled yarns by unifi

©Hytex Industries, Inc. 2010 All rights reserved.

©2008 CRYPTON, Inc. CRYPTON and the planet logo are registered trademarks of CRYPTON, Inc. U.S. patent 5,565,265 and other U.S. and global patents issued and pending.

REPREVE is a registered trademark of Unifi, Inc.



HIGH PERFORMANCE Eco-FABRIC FOR VERTICAL SURFACES

Wallcoverings • Panel Systems • Partitions

Utilizing a combination of pre-consumer and post-consumer recycled polyester to create unique performance yarns, Hytex Industries introduces our newest collection of vertical surface textiles for the commercial market.

STARRY NIGHT

SPECIFICATIONS

| <u>CONTENT</u> | <u>BACKING</u> | <u>FINISH</u> | <u>WEIGHT</u> | <u>WIDTH</u> | <u>ROLL SIZE</u> |
|---------------------------|----------------|---|---------------|--------------|------------------|
| · 100% recycled polyester | acrylic latex | Crypton® 'Green' Soil & Stain Repellant | 16 oz. | 54" | 50 yards |
| · 49% post-consumer | | | | | |
| · 51% pre-consumer | | | | | |

FLAMMABILITY

Passes: NFPA 286
Class A / ASTM E-84
Passes: Cal 117
Passes: Vertical Burn

ABRASION RESISTANCE

(ASTM D-4157-02)
100,000 double rubs

COLOR FASTNESS TO LIGHT

(AATCC-16A)
Class 5.0 / 100 hrs.

ENVIRONMENTAL

does not contain:

- pvc
- chlorene
- plasticizers
- heavy metals
- formaldehyde
- ozone depleting substances
- volatile organic chemicals (voc's)

conserving natural resources:

- diverts waste from landfills
- offsets the need to refine new crude oil
- requires less energy to produce

REPREVE®
recycled yarns by unifi

© Hytex Industries, Inc. 2009 All rights reserved.

©2008 CRYPTON, Inc. CRYPTON and the planet logo are registered trademarks of CRYPTON, Inc. U.S. patent 5,565,265 and other U.S. and global patents issued and pending.

REPREVE is a registered trademark of Unifi, Inc.



HIGH PERFORMANCE Eco-FABRIC FOR VERTICAL SURFACES

Wallcoverings • Panel Systems • Partitions

Utilizing a combination of pre-consumer and post-consumer recycled polyester to create unique performance yarns, Hytex Industries introduces our newest collection of vertical surface textiles for the commercial market.

STRIA

SPECIFICATIONS

| <u>CONTENT</u> | <u>BACKING</u> | <u>FINISH</u> | <u>WEIGHT</u> | <u>WIDTH</u> | <u>ROLL SIZE</u> |
|---------------------------|----------------|---|---------------|--------------|------------------|
| · 100% recycled polyester | acrylic latex | Crypton® 'Green' Soil & Stain Repellant | 14 oz. | 54" | 50 yards |
| · 25% post-consumer | | | | | |
| · 75% pre-consumer | | | | | |

FLAMMABILITY

Passes: NFPA 286
Class A / ASTM E-84
Passes: Cal 117
Passes: Vertical Burn

ABRASION RESISTANCE

(ASTM D-4157-02)
100,000 double rubs

COLOR FASTNESS TO LIGHT

(AATCC-16A)
Class 5.0 / 100 hrs.

ENVIRONMENTAL

does not contain:

- pvc
- chlorene
- plasticizers
- heavy metals
- formaldehyde
- ozone depleting substances
- volatile organic chemicals (voc's)

conserving natural resources:

- diverts waste from landfills
- offsets the need to refine new crude oil
- requires less energy to produce

REPREVE®

recycled yarns by unifi

© Hytex Industries, Inc. 2009 All rights reserved.

©2008 CRYPTON, Inc. CRYPTON and the planet logo are registered trademarks of CRYPTON, Inc. U.S. patent 5,565,265 and other U.S. and global patents issued and pending.

REPREVE is a registered trademark of Unifi, Inc.



Hytex Industries, Inc. · 58 York Avenue · Randolph, MA 02368-1828 · Telephone (781) 963-4400 · Fax: (781) 986-5956 · www.hytex.com

Boucle

PHYSICAL SPECIFICATIONS

- Roll Size: 50 lineal yards
- Fabric Width: 54" untrimmed
- Abrasion Resistance: 30,000 MINIMUM CYCLES
- Backing: Latex/Acrylic
- Composition: Woven of 100% polyester yarns

FINISH

Treated with Teflon® fabric protection system by Dupont. Teflon's soil and stain resistance adds years to the life of a fabric. It dramatically cuts on-site maintenance and replacement costs, making every installation a better investment for your customers.

FLAMMABILITY SPECIFICATIONS


- Meets a Class A Flame Spread Rating in accordance with ASTM E-84
- Passes Corner Burn (NFPA 265, UBC 8-2)
- Meets Vertical Burn requirements in accordance with ANSI A-17
- Cigarette Ignition: U.F.A.C. Class 1
- MEA #279-90M
- Has been tested for toxicity in accordance with Pittsburgh Protocol and is no more toxic than wood (LA₅₀ method)

| TEST SPECIMEN | FLAME SPREAD RATE | FUEL CONTRIBUTED FACTOR | SMOKE DEVELOPED FACTOR |
|-----------------------|-------------------|-------------------------|------------------------|
| Asbestos Cement Board | 0 | 0 | 0 |
| Red Oak Flooring | 100 | 100 | 100 |
| Fabric | 10 | 15 | 0 |

NOTE: The numerical flame spread rating and other test results referenced herein are not intended to reflect hazards presented by this or any other material under actual fire conditions.

PERFORMANCE SPECIFICATIONS

| Performance Test | Textile Wallcovering Standard Requirement | Inspirations Results |
|---|--|---|
| ASTM D-1682 Tensile Strength (Grab) | 50 lbs. minimum 50 lbs. minimum | Warp 190.3 lbs. Filling 210.0 lbs. |
| ASTM D-2261 Tear Strength (Tongue) | 6 lbs. minimum 6 lbs. minimum | Across warp 38.7 lbs. Across filling 19.8 lbs. |
| ASTM D-4034 Resistance to yarn slippage at seams | 25 lbs. minimum 25 lbs. minimum | Seamed across warp 85 lbs. Seamed across filling 85 lbs. |
| ASTM D-2654 Procedure #2 Moisture regain | No published standard | .5% excellent |
| AATCC 8 Colorfastness to crocking | Dry procedure Class 4 minimum Wet procedure Class 3 minimum | Class 5 (dry procedure) Class 5 (wet procedure) |
| AATCC 16A Colorfastness to light 40 hours | Class 4 minimum | Class 5 (over 100 hours) |


Teflon
fabric protector



Hytex Industries, Inc. · 58 York Avenue · Randolph, MA 02368-1828 · Telephone (781) 963-4400 · Fax: (781) 986-5956 · www.hytex.com

Capri

PHYSICAL SPECIFICATIONS

- Roll Size: 50 lineal yards
- Fabric Width: 54" untrimmed
- Abrasion Resistance: 30,000 MINIMUM CYCLES
- Backing: Latex/Acrylic
- Composition: Woven of 100% polyester yarns

FINISH

Treated with Teflon® fabric protection system by Dupont. Teflon's soil and stain resistance adds years to the life of a fabric. It dramatically cuts on-site maintenance and replacement costs, making every installation a better investment for your customers.

FLAMMABILITY SPECIFICATIONS

- *Meets a Class A Flame Spread Rating in accordance with ASTM E-84*
- *Passes Corner Burn (NFPA 265, UBC 8-2)*
- *Meets Vertical Burn requirements in accordance with ANSI A-17*
- *Cigarette Ignition: U.F.A.C. Class 1*
- *MEA #279-90M*
- *Has been tested for toxicity in accordance with Pittsburgh Protocol and is no more toxic than wood (LA₅₀ method)*

| TEST SPECIMEN | FLAME SPREAD RATE | FUEL CONTRIBUTED FACTOR | SMOKE DEVELOPED FACTOR |
|-----------------------|-------------------|-------------------------|------------------------|
| Asbestos Cement Board | 0 | 0 | 0 |
| Red Oak Flooring | 100 | 100 | 100 |
| Fabric | 10 | 15 | 0 |

NOTE: The numerical flame spread rating and other test results referenced herein are not intended to reflect hazards presented by this or any other material under actual fire conditions.

PERFORMANCE SPECIFICATIONS

| Performance Test | Textile Wallcovering Standard Requirement | Inspirations Results |
|---|--|---|
| ASTM D-1682 Tensile Strength (Grab) | 50 lbs. minimum 50 lbs. minimum | Warp 190.3 lbs. Filling 210.0 lbs. |
| ASTM D-2261 Tear Strength (Tongue) | 6 lbs. minimum 6 lbs. minimum | Across warp 38.7 lbs. Across filling 19.8 lbs. |
| ASTM D-4034 Resistance to yarn slippage at seams | 25 lbs. minimum 25 lbs. minimum | Seamed across warp 85 lbs. Seamed across filling 85 lbs. |
| ASTM D-2654 Procedure #2 Moisture regain | No published standard | .5% excellent |
| AATCC 8 Colorfastness to crocking | Dry procedure Class 4 minimum Wet procedure Class 3 minimum | Class 5 (dry procedure) Class 5 (wet procedure) |
| AATCC 16A Colorfastness to light 40 hours | Class 4 minimum | Class 5 (over 100 hours) |



Teflon
fabric protector



Hytex Industries, Inc. · 58 York Avenue · Randolph, MA 02368-1828 · Telephone (781) 963-4400 · Fax: (781) 986-5956 · www.hytex.com

Douppioni

PHYSICAL SPECIFICATIONS

- Roll Size: 50 lineal yards
- Fabric Width: 54" untrimmed
- Abrasion Resistance: 30,000 MINIMUM CYCLES
- Backing: Latex/Acrylic
- Composition: Woven of 100% polyester yarns

FINISH

Treated with Teflon® fabric protection system by Dupont. Teflon's soil and stain resistance adds years to the life of a fabric. It dramatically cuts on-site maintenance and replacement costs, making every installation a better investment for your customers.

FLAMMABILITY SPECIFICATIONS

- *Meets a Class A Flame Spread Rating in accordance with ASTM E-84*
- *Passes Corner Burn (NFPA 265, UBC 8-2)*
- *Meets Vertical Burn requirements in accordance with ANSI A-17*
- *Cigarette Ignition: U.F.A.C. Class 1*
- *MEA #279-90M*
- *Has been tested for toxicity in accordance with Pittsburgh Protocol and is no more toxic than wood (LA₅₀ method)*

| TEST SPECIMEN | FLAME SPREAD RATE | FUEL CONTRIBUTED FACTOR | SMOKE DEVELOPED FACTOR |
|-----------------------|-------------------|-------------------------|------------------------|
| Asbestos Cement Board | 0 | 0 | 0 |
| Red Oak Flooring | 100 | 100 | 100 |
| Fabric | 10 | 15 | 0 |

NOTE: The numerical flame spread rating and other test results referenced herein are not intended to reflect hazards presented by this or any other material under actual fire conditions.

PERFORMANCE SPECIFICATIONS

| Performance Test | Textile Wallcovering Standard Requirement | Inspirations Results |
|---|--|---|
| ASTM D-1682 Tensile Strength (Grab) | 50 lbs. minimum 50 lbs. minimum | Warp 190.3 lbs. Filling 210.0 lbs. |
| ASTM D-2261 Tear Strength (Tongue) | 6 lbs. minimum 6 lbs. minimum | Across warp 38.7 lbs. Across filling 19.8 lbs. |
| ASTM D-4034 Resistance to yarn slippage at seams | 25 lbs. minimum 25 lbs. minimum | Seamed across warp 85 lbs. Seamed across filling 85 lbs. |
| ASTM D-2654 Procedure #2 Moisture regain | No published standard | .5% excellent |
| AATCC 8 Colorfastness to crocking | Dry procedure Class 4 minimum Wet procedure Class 3 minimum | Class 5 (dry procedure) Class 5 (wet procedure) |
| AATCC 16A Colorfastness to light 40 hours | Class 4 minimum | Class 5 (over 100 hours) |



Teflon
fabric protector



ECHO

PHYSICAL SPECIFICATIONS

Abrasion Resistance: *Up to 36,000 minimum cycles (cotton duck)*

- Roll Size: 50 lineal yards
- Fabric Width: 54" untrimmed
- Finish: Protected by **Teflon**[®] fabric protector system by Dupont
- Backing: Acrylic latex with Stain-Guard
- Composition: 65% polyester, 35% olefin

FLAMMABILITY SPECIFICATIONS

- *Meets a Class A Flame Spread Rating in accordance with ASTM E-84*
- *Meets Vertical Burn requirements in accordance with NFPA-701*
- *Passes Corner Burn (NFPA 265, UBC 8-2)*

TEST SPECIMEN

FLAME SPREAD RATE

SMOKE DEVELOPED FACTOR

| | | |
|------------------------------------|-----|-----|
| Asbestos Cement Board | 0 | 0 |
| Red Oak Flooring | 100 | 100 |
| Fabric – over 5/8" type "X" gypsum | 20 | 50 |

NOTE: The numerical flame spread rating and other test results referenced herein are not intended to reflect hazards presented by this or any other material under actual fire conditions.

PERFORMANCE SPECIFICATIONS

| Performance Test | Textile Wallcovering Standard Requirement | Results |
|---|--|---|
| ASTM D-1682 Tensile Strength (Grab) | 50 lbs. minimum 50 lbs. minimum | Warp 97 lbs. Filling 97 lbs. |
| ASTM D-2261 Tear Strength (Tongue) | 6 lbs. minimum 6 lbs. minimum | Across warp 9 lbs. Across filling 9 lbs. |
| ASTM D-4034 Resistance to yarn slippage at seams | 25 lbs. minimum 25 lbs. minimum | Seamed across warp 88 lbs. Seamed across filling 93 lbs. |
| AATCC 8 Colorfastness to crocking | Dry procedure Class 4 minimum Wet procedure Class 3 minimum | Class 4 (dry procedure) Class 4 (wet procedure) |
| AATCC 16A Colorfastness to light 40 hours | Class 4 minimum | Class 4 (40 hours) |

ANTI-MICROBIAL PROPERTIES:

Echo is woven with 69% polyester, 39% olefin which will not mildew, rot or support the growth of bacteria and is non-allergenic.

STATIC PROPERTIES:

Echo is woven with 69% polyester, 39% olefin which has low static properties.

MAINTENANCE:

Echo is easy to clean. Depending upon the extent of soilage, use traditional cleaning methods, i.e., washing, wiping, vacuuming. If promptly treated, most indelible stains can be removed by using selected cleaning agents with no damaging effect.

INSTALLATION:

Be sure edges are even. Wall should be cleaned and primed before application. Apply a thin coating of heavy duty vinyl adhesive to the wall – not the fabric. Allow adhesive to become tacky. Apply material to wall. Be sure edges butt evenly. Roll fabric firmly.

More detailed wallcovering installation instructions are enclosed with every fabric shipment and should be carefully read prior to installation.





Hytex Industries, Inc. · 58 York Avenue · Randolph, MA 02368-1828 · Telephone (781) 963-4400 · Fax: (781) 986-5956 · www.hytex.com

Eloquence

PHYSICAL SPECIFICATIONS

- Roll Size: 50 lineal yards
- Fabric Width: 54" untrimmed
- Abrasion Resistance: 30,000 MINIMUM CYCLES
- Backing: Latex/Acrylic
- Composition: Woven of 100% polyester yarns

FINISH

Treated with Teflon® fabric protection system by Dupont. Teflon's soil and stain resistance adds years to the life of a fabric. It dramatically cuts on-site maintenance and replacement costs, making every installation a better investment for your customers.

FLAMMABILITY SPECIFICATIONS

- *Meets a Class A Flame Spread Rating in accordance with ASTM E-84*
- *Passes Corner Burn (NFPA 265, UBC 8-2)*
- *Meets Vertical Burn requirements in accordance with ANSI A-17*
- *Cigarette Ignition: U.F.A.C. Class I*
- *MEA #279-90M*
- *Has been tested for toxicity in accordance with Pittsburgh Protocol and is no more toxic than wood (LA₅₀ method)*

| TEST SPECIMEN | FLAME SPREAD RATE | FUEL CONTRIBUTED FACTOR | SMOKE DEVELOPED FACTOR |
|-----------------------|-------------------|-------------------------|------------------------|
| Asbestos Cement Board | 0 | 0 | 0 |
| Red Oak Flooring | 100 | 100 | 100 |
| Fabric | 10 | 15 | 0 |

NOTE: The numerical flame spread rating and other test results referenced herein are not intended to reflect hazards presented by this or any other material under actual fire conditions.

PERFORMANCE SPECIFICATIONS

| Performance Test | Textile Wallcovering Standard Requirement | Inspirations Results |
|---|--|---|
| ASTM D-1682 Tensile Strength (Grab) | 50 lbs. minimum 50 lbs. minimum | Warp 190.3 lbs. Filling 210.0 lbs. |
| ASTM D-2261 Tear Strength (Tongue) | 6 lbs. minimum 6 lbs. minimum | Across warp 38.7 lbs. Across filling 19.8 lbs. |
| ASTM D-4034 Resistance to yarn slippage at seams | 25 lbs. minimum 25 lbs. minimum | Seamed across warp 85 lbs. Seamed across filling 85 lbs. |
| ASTM D-2654 Procedure #2 Moisture regain | No published standard | .5% excellent |
| AATCC 8 Colorfastness to crocking | Dry procedure Class 4 minimum Wet procedure Class 3 minimum | Class 5 (dry procedure) Class 5 (wet procedure) |
| AATCC 16A Colorfastness to light 40 hours | Class 4 minimum | Class 5 (over 100 hours) |





GAZEBO

PHYSICAL SPECIFICATIONS

Abrasion Resistance: *Up to 51,000 minimum cycles (cotton duck)*

- Roll Size: 50 lineal yards
- Fabric Width: 54" untrimmed
- Finish: Protected by **Teflon**[®] fabric protector system by Dupont
- Backing: Acrylic latex with Stain-Guard
- Composition: 62% polyester, 38% olefin

FLAMMABILITY SPECIFICATIONS

- *Meets a Class A Flame Spread Rating in accordance with ASTM E-84*
- *Meets Vertical Burn requirements in accordance with NFPA-701*
- *Passes Corner Burn (NFPA 265, UBC 8-2)*

| TEST SPECIMEN | FLAME SPREAD RATE | SMOKE DEVELOPED FACTOR |
|------------------------------------|-------------------|------------------------|
| Asbestos Cement Board | 0 | 0 |
| Red Oak Flooring | 100 | 100 |
| Fabric – over 5/8" type "X" gypsum | 20 | 50 |

NOTE: The numerical flame spread rating and other test results referenced herein are not intended to reflect hazards presented by this or any other material under actual fire conditions.

PERFORMANCE SPECIFICATIONS

| Performance Test | Textile Wallcovering Standard Requirement | Results |
|---|--|---|
| ASTM D-1682 Tensile Strength (Grab) | 50 lbs. minimum 50 lbs. minimum | Warp 97 lbs. Filling 97 lbs. |
| ASTM D-2261 Tear Strength (Tongue) | 6 lbs. minimum 6 lbs. minimum | Across warp 9 lbs. Across filling 9 lbs. |
| ASTM D-4034 Resistance to yarn slippage at seams | 25 lbs. minimum 25 lbs. minimum | Seamed across warp 94 lbs. Seamed across filling 93 lbs. |
| AATCC 8 Colorfastness to crocking | Dry procedure Class 4 minimum Wet procedure Class 3 minimum | Class 4 (dry procedure) Class 4 (wet procedure) |
| AATCC 16A Colorfastness to light 40 hours | Class 4 minimum | Class 4 (40 hours) |

ANTI-MICROBIAL PROPERTIES:

Gazebo will not mildew, rot or support the growth of bacteria and is non-allergenic.

STATIC PROPERTIES:

Gazebo has low static properties.

MAINTENANCE:

Gazebo is easy to clean. Depending upon the extent of soilage, use traditional cleaning methods, i.e., washing, wiping, vacuuming. If promptly treated, most indelible stains can be removed by using selected cleaning agents with no damaging effect.

INSTALLATION:

Be sure edges are even. Wall should be cleaned and primed before application. Apply a thin coating of heavy duty vinyl adhesive to the wall – not the fabric. Allow adhesive to become tacky. Apply material to wall. Be sure edges butt evenly. Roll fabric firmly.

More detailed wallcovering installation instructions are enclosed with every fabric shipment and should be carefully read prior to installation.



GROOVE

PHYSICAL SPECIFICATIONS

Abrasion Resistance: *Up to 30,000 minimum cycles (cotton duck)*

- Roll Size: 50 lineal yards
- Fabric Width: 54" untrimmed
- Finish: Protected by **Teflon**[®] fabric protector system by Dupont
- Backing: Acrylic latex
- Composition: 100% polyester

FLAMMABILITY SPECIFICATIONS

- *Meets a Class A Flame Spread Rating in accordance with ASTM E-84*
- *Meets Vertical Burn requirements in accordance with NFPA-701*
- *Passes Corner Burn (NFPA 265, UBC 8-2)*

TEST SPECIMEN

FLAME SPREAD RATE

SMOKE DEVELOPED FACTOR

| | | |
|------------------------------------|-----|-----|
| Asbestos Cement Board | 0 | 0 |
| Red Oak Flooring | 100 | 100 |
| Fabric – over 5/8" type "X" gypsum | 20 | 50 |

NOTE: The numerical flame spread rating and other test results referenced herein are not intended to reflect hazards presented by this or any other material under actual fire conditions.

PERFORMANCE SPECIFICATIONS

| Performance Test | Textile Wallcovering Standard Requirement | Results |
|---|--|---|
| ASTM D-1682 Tensile Strength (Grab) | 50 lbs. minimum 50 lbs. minimum | Warp 50 lbs. Filling 50 lbs. |
| ASTM D-2261 Tear Strength (Tongue) | 6 lbs. minimum 6 lbs. minimum | Across warp 9 lbs. Across filling 9 lbs. |
| ASTM D-4034 Resistance to yarn slippage at seams | 25 lbs. minimum 25 lbs. minimum | Seamed across warp 50 lbs. Seamed across filling 50 lbs. |
| AATCC 8 Colorfastness to crocking | Dry procedure Class 4 minimum Wet procedure Class 3 minimum | Class 4 (dry procedure) Class 4 (wet procedure) |
| AATCC 16A Colorfastness to light 40 hours | Class 4 minimum | Class 4 (40 hours) |

ANTI-MICROBIAL PROPERTIES:

Groove is woven with 100% polyester which will not mildew, rot or support the growth of bacteria and is non-allergenic.

STATIC PROPERTIES:

Groove is woven with 100% polyester which has Low static properties.

MAINTENANCE:

Groove is easy to clean. Depending upon the extent of soilage, use traditional cleaning methods, i.e., washing, wiping, vacuuming. If promptly treated, most indelible stains can be removed by using selected cleaning agents with no damaging effect.

INSTALLATION:

Be sure edges are even. Wall should be cleaned and primed before application. Apply a thin coating of heavy duty vinyl adhesive to the wall – not the fabric. Allow adhesive to become tacky. Apply material to wall. Be sure edges butt evenly. Roll fabric firmly.

More detailed wallcovering installation instructions are enclosed with every fabric shipment and should be carefully read prior to installation.


Teflon[®]
fabric protector

HYTEX

HUSTLE

PHYSICAL SPECIFICATIONS

Abrasion Resistance: *Up to 30,000 minimum cycles (cotton duck)*

- Roll Size: 50 lineal yards
- Fabric Width: 54" untrimmed
- Finish: Protected by **Teflon**® fabric protector system by Dupont
- Backing: Acrylic latex
- Composition: 100% polyester

FLAMMABILITY SPECIFICATIONS

- *Meets a Class A Flame Spread Rating in accordance with ASTM E-84*
- *Meets Vertical Burn requirements in accordance with NFPA-701*
- *Passes Corner Burn (NFPA 265, UBC 8-2)*

| TEST SPECIMEN | FLAME SPREAD RATE | SMOKE DEVELOPED FACTOR |
|------------------------------------|-------------------|------------------------|
| Asbestos Cement Board | 0 | 0 |
| Red Oak Flooring | 100 | 100 |
| Fabric – over 5/8" type "X" gypsum | 20 | 50 |

NOTE: The numerical flame spread rating and other test results referenced herein are not intended to reflect hazards presented by this or any other material under actual fire conditions.

PERFORMANCE SPECIFICATIONS

| Performance Test | Textile Wallcovering Standard Requirement | Results |
|--------------------------------------|---|-------------------------------|
| ASTM D-1682 | 50 lbs. minimum | Warp 50 lbs. |
| Tensile Strength (Grab) | 50 lbs. minimum | Filling 50 lbs. |
| ASTM D-2261 | 6 lbs. minimum | Across warp 9 lbs. |
| Tear Strength (Tongue) | 6 lbs. minimum | Across filling 9 lbs. |
| ASTM D-4034 | 25 lbs. minimum | Seamed across warp 50 lbs. |
| Resistance to yarn slippage at seams | 25 lbs. minimum | Seamed across filling 50 lbs. |
| AATCC 8 | Dry procedure Class 4 minimum | Class 4 (dry procedure) |
| Colorfastness to crocking | Wet procedure Class 3 minimum | Class 4 (wet procedure) |
| AATCC 16A | Class 4 minimum | Class 4 (40 hours) |
| Colorfastness to light 40 hours | | |

ANTI-MICROBIAL PROPERTIES:

Hustle is woven with 100% polyester which will not mildew, rot or support the growth of bacteria and is non-allergenic.

STATIC PROPERTIES:

Hustle is woven with 100% polyester which has low static properties.

MAINTENANCE:

Hustle is easy to clean. Depending upon the extent of soilage, use traditional cleaning methods, i.e., washing, wiping, vacuuming. If promptly treated, most indelible stains can be removed by using selected cleaning agents with no damaging effect.

INSTALLATION:

Be sure edges are even. Wall should be cleaned and primed before application. Apply a thin coating of heavy duty vinyl adhesive to the wall – not the fabric. Allow adhesive to become tacky. Apply material to wall. Be sure edges butt evenly. Roll fabric firmly.

More detailed wallcovering installation instructions are enclosed with every fabric shipment and should be carefully read prior to installation.



Teflon
fabric protector



Hytex Industries, Inc. · 58 York Avenue · Randolph, MA 02368-1828 · Telephone (781) 963-4400 · Fax: (781) 986-5956 · www.hytex.com

Illumination

PHYSICAL SPECIFICATIONS

- Roll Size: 50 lineal yards
- Fabric Width: 54" untrimmed
- Abrasion Resistance: 30,000 MINIMUM CYCLES
- Backing: Latex/Acrylic
- Composition: Woven of 100% polyester yarns

FINISH

Treated with Teflon® fabric protection system by Dupont. Teflon's soil and stain resistance adds years to the life of a fabric. It dramatically cuts on-site maintenance and replacement costs, making every installation a better investment for your customers.

FLAMMABILITY SPECIFICATIONS

- *Meets a Class A Flame Spread Rating in accordance with ASTM E-84*
- *Passes Corner Burn (NFPA 265, UBC 8-2)*
- *Meets Vertical Burn requirements in accordance with ANSI A-17*
- *Cigarette Ignition: U.F.A.C. Class I*
- *MEA #279-90M*
- *Has been tested for toxicity in accordance with Pittsburgh Protocol and is no more toxic than wood (LA₅₀ method)*

| TEST SPECIMEN | FLAME SPREAD RATE | FUEL CONTRIBUTED FACTOR | SMOKE DEVELOPED FACTOR |
|-----------------------|-------------------|-------------------------|------------------------|
| Asbestos Cement Board | 0 | 0 | 0 |
| Red Oak Flooring | 100 | 100 | 100 |
| Fabric | 10 | 15 | 0 |

NOTE: The numerical flame spread rating and other test results referenced herein are not intended to reflect hazards presented by this or any other material under actual fire conditions.

PERFORMANCE SPECIFICATIONS

| Performance Test | Textile Wallcovering Standard Requirement | Inspirations Results |
|---|--|---|
| ASTM D-1682 Tensile Strength (Grab) | 50 lbs. minimum 50 lbs. minimum | Warp 190.3 lbs. Filling 210.0 lbs. |
| ASTM D-2261 Tear Strength (Tongue) | 6 lbs. minimum 6 lbs. minimum | Across warp 38.7 lbs. Across filling 19.8 lbs. |
| ASTM D-4034 Resistance to yarn slippage at seams | 25 lbs. minimum 25 lbs. minimum | Seamed across warp 85 lbs. Seamed across filling 85 lbs. |
| ASTM D-2654 Procedure #2 Moisture regain | No published standard | .5% excellent |
| AATCC 8 Colorfastness to crocking | Dry procedure Class 4 minimum Wet procedure Class 3 minimum | Class 5 (dry procedure) Class 5 (wet procedure) |
| AATCC 16A Colorfastness to light 40 hours | Class 4 minimum | Class 5 (over 100 hours) |



Teflon
fabric protector



Hytex Industries, Inc. · 58 York Avenue · Randolph, MA 02368-1828 · Telephone (781) 963-4400 · Fax: (781) 986-5956 · www.hytex.com

Infinity

PHYSICAL SPECIFICATIONS

- Roll Size: 50 lineal yards
- Fabric Width: 54" untrimmed
- Abrasion Resistance: 30,000 MINIMUM CYCLES
- Backing: Latex/Acrylic
- Composition: Woven of olefin & polyester yarns

FINISH

Treated with Teflon® fabric protection system by Dupont. Teflon's soil and stain resistance adds years to the life of a fabric. It dramatically cuts on-site maintenance and replacement costs, making every installation a better investment for your customers.

FLAMMABILITY SPECIFICATIONS

- Meets a Class A Flame Spread Rating in accordance with ASTM E-84
- Passes Corner Burn (NFPA 265, UBC 8-2)
- Meets Vertical Burn requirements in accordance with ANSI A-17
- Cigarette Ignition: U.F.A.C. Class I
- MEA #279-90M
- Has been tested for toxicity in accordance with Pittsburgh Protocol and is no more toxic than wood (LA₅₀ method)

| TEST SPECIMEN | FLAME SPREAD RATE | FUEL CONTRIBUTED FACTOR | SMOKE DEVELOPED FACTOR |
|-----------------------|-------------------|-------------------------|------------------------|
| Asbestos Cement Board | 0 | 0 | 0 |
| Red Oak Flooring | 100 | 100 | 100 |
| Fabric | 10 | 15 | 0 |

NOTE: The numerical flame spread rating and other test results referenced herein are not intended to reflect hazards presented by this or any other material under actual fire conditions.

PERFORMANCE SPECIFICATIONS

| Performance Test | Textile Wallcovering Standard Requirement | Inspirations Results |
|---|--|---|
| ASTM D-1682 Tensile Strength (Grab) | 50 lbs. minimum 50 lbs. minimum | Warp 190.3 lbs. Filling 210.0 lbs. |
| ASTM D-2261 Tear Strength (Tongue) | 6 lbs. minimum 6 lbs. minimum | Across warp 38.7 lbs. Across filling 19.8 lbs. |
| ASTM D-4034 Resistance to yarn slippage at seams | 25 lbs. minimum 25 lbs. minimum | Seamed across warp 85 lbs. Seamed across filling 85 lbs. |
| ASTM D-2654 Procedure #2 Moisture regain | No published standard | .5% excellent |
| AATCC 8 Colorfastness to crocking | Dry procedure Class 4 minimum Wet procedure Class 3 minimum | Class 5 (dry procedure) Class 5 (wet procedure) |
| AATCC 16A Colorfastness to light 40 hours | Class 4 minimum | Class 5 (over 100 hours) |



Teflon
fabric protector



Hytex Industries, Inc. · 58 York Avenue · Randolph, MA 02368-1828 · Telephone (781) 963-4400 · Fax: (781) 986-5956 · www.hytex.com

Luxuriant

PHYSICAL SPECIFICATIONS

- Roll Size: 50 lineal yards
- Fabric Width: 54" untrimmed
- Abrasion Resistance: 30,000 MINIMUM CYCLES
- Backing: Latex/Acrylic
- Composition: Woven of 100% polyester yarns

FINISH

Treated with Teflon® fabric protection system by Dupont. Teflon's soil and stain resistance adds years to the life of a fabric. It dramatically cuts on-site maintenance and replacement costs, making every installation a better investment for your customers.

FLAMMABILITY SPECIFICATIONS

- Meets a Class A Flame Spread Rating in accordance with ASTM E-84
- Passes Corner Burn (NFPA 265, UBC 8-2)
- Meets Vertical Burn requirements in accordance with ANSI A-17
- Cigarette Ignition: U.F.A.C. Class 1
- MEA #279-90M
- Has been tested for toxicity in accordance with Pittsburgh Protocol and is no more toxic than wood (LA₅₀ method)

| TEST SPECIMEN | FLAME SPREAD RATE | FUEL CONTRIBUTED FACTOR | SMOKE DEVELOPED FACTOR |
|-----------------------|-------------------|-------------------------|------------------------|
| Asbestos Cement Board | 0 | 0 | 0 |
| Red Oak Flooring | 100 | 100 | 100 |
| Fabric | 10 | 15 | 0 |

NOTE: The numerical flame spread rating and other test results referenced herein are not intended to reflect hazards presented by this or any other material under actual fire conditions.

PERFORMANCE SPECIFICATIONS

| Performance Test | Textile Wallcovering Standard Requirement | Inspirations Results |
|---|--|---|
| ASTM D-1682 Tensile Strength (Grab) | 50 lbs. minimum 50 lbs. minimum | Warp 190.3 lbs. Filling 210.0 lbs. |
| ASTM D-2261 Tear Strength (Tongue) | 6 lbs. minimum 6 lbs. minimum | Across warp 38.7 lbs. Across filling 19.8 lbs. |
| ASTM D-4034 Resistance to yarn slippage at seams | 25 lbs. minimum 25 lbs. minimum | Seamed across warp 85 lbs. Seamed across filling 85 lbs. |
| ASTM D-2654 Procedure #2 Moisture regain | No published standard | .5% excellent |
| AATCC 8 Colorfastness to crocking | Dry procedure Class 4 minimum Wet procedure Class 3 minimum | Class 5 (dry procedure) Class 5 (wet procedure) |
| AATCC 16A Colorfastness to light 40 hours | Class 4 minimum | Class 5 (over 100 hours) |



Teflon
fabric protector



Hytex Industries, Inc. · 58 York Avenue · Randolph, MA 02368-1828 · Telephone (781) 963-4400 · Fax: (781) 986-5956 · www.hytex.com

Matelasse

PHYSICAL SPECIFICATIONS

- Roll Size: 50 lineal yards
- Fabric Width: 54" untrimmed
- Abrasion Resistance: 20,000 MINIMUM CYCLES
- Backing: Latex/Acrylic
- Composition: Woven of 100% polyester yarns

FINISH

Treated with Teflon® fabric protection system by Dupont. Teflon's soil and stain resistance adds years to the life of a fabric. It dramatically cuts on-site maintenance and replacement costs, making every installation a better investment for your customers.

FLAMMABILITY SPECIFICATIONS

| | |
|---|--|
| • <i>Meets a Class A Flame Spread Rating in accordance with ASTM E-84</i> | • <i>Cigarette Ignition: U.F.A.C. Class 1</i> |
| • <i>Passes Corner Burn (NFPA 265, UBC 8-2)</i> | • <i>MEA #279-90M</i> |
| • <i>Meets Vertical Burn requirements in accordance with ANSI A-17</i> | • <i>Has been tested for toxicity in accordance with Pittsburgh Protocol and is no more toxic than wood (LA₅₀ method)</i> |

| TEST SPECIMEN | FLAME SPREAD RATE | FUEL CONTRIBUTED FACTOR | SMOKE DEVELOPED FACTOR |
|-----------------------|-------------------|-------------------------|------------------------|
| Asbestos Cement Board | 0 | 0 | 0 |
| Red Oak Flooring | 100 | 100 | 100 |
| Fabric | 10 | 15 | 0 |

NOTE: The numerical flame spread rating and other test results referenced herein are not intended to reflect hazards presented by this or any other material under actual fire conditions.

PERFORMANCE SPECIFICATIONS

| Performance Test | Textile Wallcovering Standard Requirement | Inspirations Results |
|---|--|---|
| ASTM D-1682 Tensile Strength (Grab) | 50 lbs. minimum 50 lbs. minimum | Warp 190.3 lbs. Filling 210.0 lbs. |
| ASTM D-2261 Tear Strength (Tongue) | 6 lbs. minimum 6 lbs. minimum | Across warp 38.7 lbs. Across filling 19.8 lbs. |
| ASTM D-4034 Resistance to yarn slippage at seams | 25 lbs. minimum 25 lbs. minimum | Seamed across warp 85 lbs. Seamed across filling 85 lbs. |
| ASTM D-2654 Procedure #2 Moisture regain | No published standard | .5% excellent |
| AATCC 8 Colorfastness to crocking | Dry procedure Class 4 minimum Wet procedure Class 3 minimum | Class 5 (dry procedure) Class 5 (wet procedure) |
| AATCC 16A Colorfastness to light 40 hours | Class 4 minimum | Class 5 (over 100 hours) |





Hytex Industries, Inc. · 58 York Avenue · Randolph, MA 02368-1828 · Telephone (781) 963-4400 · Fax: (781) 986-5956 · www.hytex.com

Valiance

PHYSICAL SPECIFICATIONS

- Roll Size: 50 lineal yards
- Fabric Width: 54" untrimmed
- Abrasion Resistance: 30,000 MINIMUM CYCLES
- Backing: Latex/Acrylic
- Composition: Woven of 100% polyester yarns

FINISH

Treated with Teflon® fabric protection system by Dupont. Teflon's soil and stain resistance adds years to the life of a fabric. It dramatically cuts on-site maintenance and replacement costs, making every installation a better investment for your customers.

FLAMMABILITY SPECIFICATIONS

| | |
|---|--|
| • <i>Meets a Class A Flame Spread Rating in accordance with ASTM E-84</i> | • <i>Cigarette Ignition: U.F.A.C. Class 1</i> |
| • <i>Passes Corner Burn (NFPA 265, UBC 8-2)</i> | • <i>MEA #279-90M</i> |
| • <i>Meets Vertical Burn requirements in accordance with ANSI A-17</i> | • <i>Has been tested for toxicity in accordance with Pittsburgh Protocol and is no more toxic than wood (LA₅₀ method)</i> |

| TEST SPECIMEN | FLAME SPREAD RATE | FUEL CONTRIBUTED FACTOR | SMOKE DEVELOPED FACTOR |
|-----------------------|-------------------|-------------------------|------------------------|
| Asbestos Cement Board | 0 | 0 | 0 |
| Red Oak Flooring | 100 | 100 | 100 |
| Fabric | 10 | 15 | 0 |

NOTE: The numerical flame spread rating and other test results referenced herein are not intended to reflect hazards presented by this or any other material under actual fire conditions.

PERFORMANCE SPECIFICATIONS

| Performance Test | Textile Wallcovering Standard Requirement | Inspirations Results |
|---|--|---|
| ASTM D-1682 Tensile Strength (Grab) | 50 lbs. minimum 50 lbs. minimum | Warp 190.3 lbs. Filling 210.0 lbs. |
| ASTM D-2261 Tear Strength (Tongue) | 6 lbs. minimum 6 lbs. minimum | Across warp 38.7 lbs. Across filling 19.8 lbs. |
| ASTM D-4034 Resistance to yarn slippage at seams | 25 lbs. minimum 25 lbs. minimum | Seamed across warp 85 lbs. Seamed across filling 85 lbs. |
| ASTM D-2654 Procedure #2 Moisture regain | No published standard | .5% excellent |
| AATCC 8 Colorfastness to crocking | Dry procedure Class 4 minimum Wet procedure Class 3 minimum | Class 5 (dry procedure) Class 5 (wet procedure) |
| AATCC 16A Colorfastness to light 40 hours | Class 4 minimum | Class 5 (over 100 hours) |



Teflon
fabric protector